

Test Report

Report No. A224052793610100102

Page 1 of 3

Company Name SHANGHAI WALLIS TECHNOLOGY CO.,LTD
Address NO.912 YECHENG ROAD, JIADING INDUSTRY AREA,
SHANGHAI, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the
behalf of the client

Sample Name PET-G membrane
Sample Received Date Aug. 28, 2024
Testing Period Aug. 28, 2024-Sep. 5, 2024

Test Requested

No.	Test Item
1	Tear resistance

Test Result(s): Please see the following pages.

Approved by

Aeo Lin

Date

Sep. 5, 2024

Aeo Lin

Approved Signatory

No. R9F6ECAD44

Centre Testing International Group Co., Ltd.

Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

Test Report


Report No. A224052793610100102

Page 2 of 3

Tested Sample(s)

Sample No.	Sample Name
A2240527936101001	PET-G membrane

Sample Photo(s)



A2240527936101001



Test Report

Report No. A224052793610100102

Page 3 of 3

Test Item: Tear resistance**1. Test Equipment**

Equipment Name	Model
Material testing machine	34TM-50

2. Environmental Conditions

Temperature: 23±2℃, Humidity: 50±5%RH

3. Test Standard: QB/T 1130-1991**4. Test Condition**

Test speed : 200 mm/min

5. Test Result(s)

Test Sample		Test Results (kN/m)	
		Crosswise	Vertical
A2240527936101001	1	140	220
	2	170	190
	3	150	200
	4	160	220
	5	150	210
	Ave.	150	210
Specification		≥45	≥45
Conclusion		Pass	Pass

Remark: Specification was supplied by client.

Statement:

- 1.This report is considered invalid without approved signature, special seal and the seal on the perforation;
- 2.The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;
- 3.The result(s) shown in this report refer(s) only to the sample(s) tested;
- 4.Without written approval of CTI, this report can't be reproduced except in full;
- 5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** End of Report ***

